

Nimble Gloss 1700

Single pack superfast drying coating



Product Description

LP Nimble Gloss 1700 is a superfast drying topcoat developed with use of specialized modified polyester polymer. It is single pack, oxidative drying quick setting coating which can be used where fast productivity is required, specially recommended for conveyer belt applications. This product will provide rich high gloss finish, excellent adhesion, good flexibility and smooth highly durable finish. This product can be used at interior as well as exterior substrates.

Typical Use

It is recommended for use on metal substrates like carbon steel, aluminum and tin on both interior and external areas. This product is specially recommended to be applied on metal materials used in scaffoldings.

Technical Data

% Solids By Weight (NVM)	53 +/- 2		
% Solids By Volume	48 +/- 2		
Colour	Brilliant White and shades		
Gloss @ 60 G. H.	Above 90		
Specific Gravity (Density/WPL) kg/L	1.10 +/- 0.2 (For White Only)		
Flash Point	≥25°C		
VOC gm/L	≤495		
Theoretical Coverage m ² /L	Max	Min	STD
	16.0	9.6	12.0
Dry Film Thickness (DFT in microns)	30	50	40
Wet Film Thickness (WFT in microns)	63	105	85
Mixing Ratio	NA. Single Pack Product		
Thinner Intake	Spraying: 20 – 30%, Dipping:100% (QD Thinner #12)		
Pot Life @ 30°C	NA. Single Pack Product		
Drying Characteristics @ 30°C & ≤85% Humidity			
Surface Dry	5 -- 8 Minutes		
Tack Free	15 -- 20 Minutes		
Full Cure (Min.)	16 Hours		
Recoating Time (Min.)	2 hours		
Recoating Time (Max.)	Infinite		
Shelf Life & Storage	12 Months <i>Keep the containers in a dry, cool, well ventilated space and away from direct sunlight, sources of heat and ignition. Containers must be always kept tightly closed.</i>		
Pack Size	4L, 20L		

Nimble Gloss 1700

Single pack superfast drying coating



Application Guidelines

- **Surface Preparation:**

Substrate shall be clean. Traces of dust, rust, wax, oil, grease, loose particles, flakes and other contaminants shall be removed with the use of proper cleaning solvent as mentioned in the SSPC-SP1. Light sanding with abrasive material is recommended, resulting dust should be removed properly. Surface to be recoated should clean thoroughly before application.

- **Paint System:**

QD Primer 1500: 1 Coat

Nimble Gloss 1700: 1 -- 2 Coats

- **Application Tools:**

1. Conventional Air Spray : Add up to 40% QD Thinner 12
2. Dipping : Add up to 100% QD Thinner 12
3. Brush or Roller : Recommended. Care should be taken to achieve recommended DFT.

- Air Pressure: 40 – 50 bar
- Tip Size of spray gun: 1.2mm
- Ensure adequate ventilation while spraying and drying
- Substrate temperature must be 3°C above dew point

Health & Safety Measures

(Recommended to Read this section before application)

- Keep out of reach of children
- Recommended to wear overalls, safety goggles and solvent mask while spraying
- Avoid contact with skin and eyes.

First-Aid

- **Eyes** : Immediately flush eyes with water and seek medical help
- **Skin** : Use soap & water or appropriate cleaner
- **Inhalation** : Allow to breath fresh air, loose the neckline and keep him/her rested
- **Ingestion** : Obtain medical help without asking for omitting

Disclaimer

The data provided in this sheet is given to the best of our knowledge and based on laboratory testing and practical experience. We cannot guarantee anything but the product since the conditions and methods during application vary. We reserve the right to change the given data without prior notice. The product data sheet supersedes those previously issued.

For more information, contact our Liberty Paints Representative or go to www.libertypaintsarabia.com or reach to us on support@lparabia.com